

ELEME PETROCHEMICALS COMPANY LIMITED**TECHNICAL DATA SHEET****INDORAMA – LINEAR****NGL010FG**

LINEAR LOW DENSITY PE GRADE FOR FILM APPLICATION

NGL010FG is a Butene Co-monomer based Linear Low Density Polyethylene (LLDPE) Resin manufactured by EPCL using "SCLAIRTECH" solution polymerization process of DU Pont, Canada (Now Nova Chemicals) offers narrow molecular weight distribution copolymer without slip & anti-block additive which has been specifically designed for the production of high strength blown film of various thickness for monolayer, multilayer & lamination film application.

TYPICAL CHARACTERISTICS:

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	gm/10 min.	1.0
Density	ASTM D 792	gm/cm ³	0.919
Tensile Strength at Yield (MD/TD)	ASTM D 882	Mpa	12.5 / 12.0
Ultimate Tensile Strength (MD/TD)	ASTM D 882	Mpa	38 / 30
Elongation at Break (MD/TD)	ASTM D 882	%	650 / 800
Dart Impact Test	ASTM D 1709	g/μm	3.5
Tear Strength (MD/TD)	ASTM D 1922	g/μm	3.3 / 10.3

Above values are not to be construed as specifications.

PRODUCT BENEFITS

- Excellent optical properties
- Excellent seal-ability
- Good puncture resistance
- Good tear and dart impact strength
- Low gel level

APPLICATIONS

- Stretch Film
- Co-extruded film
- Lamination Films
- Agriculture use

PACKAGING: NGL010FG is available in natural colour, pallets form in 25 Kg bags.

FOOD CONTACT APPLICATIONS: This grade meets with the requirements of FDA on specifications for Polyethylene and its copolymers for its safe use in contact with foodstuffs, pharmaceuticals and drinking water.

The data, information and suggestions given herein are purely as a guide. EPCL undertakes no responsibility either for the results derived from their adoption or for possible positions in apparent contrast with existing patent rights.

ELEME PETROCHEMICALS COMPANY LIMITED**TECHNICAL DATA SHEET****SAFETY**

The Material Safety Data Sheet (MSDS) contains information regarding health, safety and waste considerations for all EPCL Liner Low Density Polyethylene grades. We urge each customer or recipient of MSDS to study it carefully to become aware of and understand the hazards associated with the product. The customer should consider consulting reference works or individuals who are experts in ventilation, toxicology or fire prevention, as necessary or appropriate to use and understand the data contained in the MSDS.

STORAGE

The material is packed in 25 kg bags protecting it from contamination. Storage times of natural materials longer than 6 months may have a negative influence on the quality of the final product. It is generally recommended to convert all material latest within 6 months of production. The material is subjected to degradation by ultra-violet radiation or by high storage temperatures. Therefore the material must be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Further unfavorable storage conditions are large fluctuations in ambient temperature and high atmospheric humidity. These conditions may lead to moisture condensing inside the packaging. Under these circumstances, it is recommended to dry the material before use. After a storage period of more than 3 months drying of such material is recommended as standard practice.

DISCLAIMER

"The information in this publication is submitted without prejudice, and is based on our current knowledge and experience and on a limited number of tests." In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication.

Export Sales

Chirag Jesalpura
Mobile: +2348052307986
E-mail: export@indorama.com.ng

Customer Services

Krishan Kant Verma
Mobile: +2348129124582
E-mail: techsupport@indorama.com.ng

Lagos

12th Floor, Zenon House,
Ajose Adeogun Street,
Victoria Island, Lagos
E-mail: lgsales@indorama.com.ng
+2348055200738

Port Harcourt

EPCL Complex,
PMB 5151, Port Harcourt,
Rivers State
E-mail: phcsales@indorama.com.ng
+2348057700089

Kano

No. 6, Niger Street,
Dakata
Kano
E-mail: kanosales@indorama.com.ng
+2348056009023

www.indoramaepcl.com

The data, information and suggestions given herein are purely as a guide. EPCL undertakes no responsibility either for the results derived from their adoption or for possible positions in apparent contrast with existing patent rights.

January 2012